Nondestructive Testing of the Corrosive Damage of Reinforced Concrete Structures Using Ultrasonic Method

Ming-Te Liang

Associate Professor, Department of Harbor and River Engineering, National Taiwan Ocean University, Keelung, Taiwan, R.O.C.

Run Huang

Associate Professor, Department of Harbor and River Engineering, National Taiwan Ocean University, Keelung, Taiwan, R.O.C.

Chii-Ming Jiang

Graduate Student, Department of Harbor and River Engineering, National Taiwan Ocean University, Keelung, Taiwan, R.O.C.

Follow this and additional works at: <https://jmstt.ntou.edu.tw/journal>

Part of the [Civil and Environmental Engineering Commons](#)

Recommended Citation

Liang, Ming-Te; Huang, Run; and Jiang, Chii-Ming (1996) "Nondestructive Testing of the Corrosive Damage of Reinforced Concrete Structures Using Ultrasonic Method," *Journal of Marine Science and Technology*: Vol. 4: Iss. 1, Article 14.

DOI: 10.51400/2709-6998.2547

Available at: <https://jmstt.ntou.edu.tw/journal/vol4/iss1/14>

This Research Article is brought to you for free and open access by Journal of Marine Science and Technology. It has been accepted for inclusion in Journal of Marine Science and Technology by an authorized editor of Journal of Marine Science and Technology.

NONDESTRUCTIVE TESTING OF THE CORROSIVE DAMAGE OF REINFORCED CONCRETE STRUCTURES USING ULTRASONIC METHOD

Ming-Te Liang*, Run Huang*, and Chii-Ming Jiang**

Keywords: amplitude, energy decay, pulse velocity.

ABSTRACT

The purpose of this study is to determine the corrosive damage of reinforced concrete members using the ultrasonic technique. The ultrasonic tester (type ULCON 3) connected the touched vertical-beam dictator (frequency: 50kHz, diameter=20mm) is used to measure the velocity and scan the concrete surface for predicting the corrosive damage. When the rebars are corroded, the ultrasonic wave propagation will very due to energy decay and velocity change. Based on the ultrasonic pulse velocity and amplitude, the structural quality of reinforced concrete can be predicted. Some results obtained from this investigation are described as follows: (1) The amplitude of reflective wave reduces if steel corrosion occurs in the RC structures, (2) Both the ultrasonic pulse velocity and amplitude can be used to evaluate the steel corrosion in the RC structures, (3) If in-site technique is developed, the life-cycle of the RC structures may be justified.

INTRODUCTION

Taiwan is surrounded by the sea. Most of the important and large civil structures are nearly the coast. The chloride ion content in the air is relatively high. The corrosion rate of reinforced concrete may be affected by the chloride diffusion so that the life-cycle of the structures is shortened. Thus, it is necessary to predict the corrosive state using nondestructive technique for quality assurance. The corrosion of reinforced concrete is very difficult to detect in the beginning. When the rust is found on the concrete surface, the structures may be severely damage. However, a reliable, accurate and fast nondestructive testing method for evaluating the internal corrosion of reinforced concrete structure is still not developed.

When the reinforced concrete structures suffer from corrosive damage, one can use some techniques to detect the deterioration. These methods include (1) the electric method-measure the natural electric potential. (2) magnetic analysis - detect the phase difference between the magnetic-current and the secondary-current occurs in steel. (3) X-ray - take the X-ray photograph for predicting the corrosive damage.

The use of the ultrasonic pulse technique for detecting integrity of concrete and steel structures is very common. Chung [1] pointed out that if ultrasonic wave propagation path is vertical to the steel, then the wave velocity in reinforced concrete should be modified. Bungey [2] showed that if the sum of steel diameter is less than 20 mm, the influence of steel can be neglected. Burdekin et al. [3] used the ultrasonic pulse amplitude to detect the reinforced concrete beam. It was founded that the amplitude of steel after corrosion was lower than the amplitude of steel without corrosion. This study uses the ultrasonic method to diagnose the corrosive damage of reinforced concrete structures.

BASIC PRINCIPLE

The transmission velocity of ultrasonic wave propagation in matter is called sound velocity. The sound velocity related to frequency and wave length is

$$C = f\lambda, \quad (1)$$

in which C = sound velocity (km/sec), f = frequency (MHz), λ = wave length (mm).

The sound velocity in particular material approaches to a constant value. However, when ultrasonic wave transmits from A materials to B materials, partly wave is reflective to A materials and partly wave is incident into B materials. Let Z_A and Z_B are respectively the impedance of material A and B. p_e , p_r , and p_d are respectively the incident, reflective

Paper Received May, 1995. Revised June, 1996. Accepted June, 1996.
Author for Correspondence: Ming-Te Liang.

*Associate Professor, Department of Harbor and River Engineering,
National Taiwan Ocean University, Keelung, Taiwan, R.O.C.

**Graduate Student, Department of Harbor and River Engineering,
National Taiwan Ocean University, Keelung, Taiwan, R.O.C.

and transmission wave pressure. Their relationship is

$$\frac{p_r}{p_e} = R, \quad (2)$$

$$\frac{p_d}{p_e} = D, \quad (3)$$

in which R and D is respectively called reflective and transmission coefficient. Use the impedance of difference material at interface to compute

$$R = \frac{Z_2 - Z_1}{Z_2 + Z_1}, \quad (4)$$

$$D = \frac{2Z_2}{Z_2 + Z_1}. \quad (5)$$

The equation of equilibrium of sound pressure is

$$p_r + p_e = p_d \text{ or } 1 + R = D \quad (6)$$

In order to detect the behavior of reinforced concrete by using the ultrasonic technique. Application of ultrasonic pulse velocity to predicting whether the steel corrosion of reinforced concrete or not is described in the following:

Chung and Law [4] considered that when ultrasonic pulse propagates in concrete, the passing time is the sum of pulse through the coarse aggregate, fine aggregate and cement paste. Let L_C , L_1 , L_2 and L_P are respectively denoted the passing length in corresponding ultrasonic pulse velocity is respectively V_C , V_1 , V_2 and V_P . Hence:

$$L_C = L_1 + L_2 + L_P, \quad (7)$$

$$\frac{L_C}{V_C} = \frac{L_1}{V_1} + \frac{L_2}{V_2} + \frac{L_P}{V_P}. \quad (8)$$

However,

$$L_1 = KA_1 L_P, \quad (9)$$

$$L_2 = KA_2 L_P. \quad (10)$$

in which K is test constant ($K=0.3$ for experience value), A_1 is the volume ratio of coarse aggregate to cement paste, A_2 is the volume ratio of fine aggregate to cement paste. From Eqs. (7) and (8), one gets

$$V_P = \frac{1}{\frac{1 + KA_1 + KA_2}{V_C} - \frac{KA_1}{V_1} - \frac{KA_2}{V_2}}. \quad (11)$$

When ultrasonic pulse propagates in the reinforced concrete, the wave velocity is

$$V_e = \frac{L_e}{\frac{L_C}{V_C} + \frac{L_s}{V_s}}, \quad (12)$$

in which L_e and L_s are respectively reinforced concrete and steel length, V_s is the wave velocity in steel.

Chung [1] pointed out that when wave path is vertical to steel, the wave velocity of reinforced concrete is

$$V_e = V_s - 10.4 \times \frac{V_s - V_C}{d}, \quad (13)$$

in which V_e , V_C and V_s are respectively the wave velocity of reinforced concrete, concrete and steel, d is the diameter of steel.

British Standard institution [5] suggested that when the ultrasonic pulse propagates vertically the steel direction, the measured velocity must be multiplied a modified coefficient according to the ratio of sum of steel diameter (L_s) to total pass length (L).

EXPERIMENTAL PROGRAM

Table 1 indicates the test sample size. Figure 1 shows the test equipments of ultrasonic pulse velocity and amplitude. For the ultrasonic pulse velocity, turn the decay control gate on the line of wave front

Fig. 1. Test equipment.

Table 1. Test sample size

Sample kind	Without corrosion	With corrosion
Sample diameter (cm)	10,12,15	10,12,15
Sample length (cm)	20	20
Steel number (#)	4,5,8	4,5,8

and adjust the velocity button so that numerical indicator shows sample length. Finally, turn DIS to VEL from transducer to get velocity. In the case of the ultrasonic pulse amplitude, firstly place the dry column sample on the rotational disk and turn the ultrasonic tester to zero and then counterclockwise it for beginning scan. The scanner will turn up 0.508cm after rotational disk taking a round. The ultrasonic tester associated with C-SCAN Signal Analysis and Display (Version 4) software acquires the percent of amplitude of reflective wave. This percent can be shown on the screen with different color (see Figure 2). The amplitude graph obtained from C-SCAN can be used to predict the corrosive damage of reinforced concrete cylinder.

RESULTS AND ANALYSIS

Ultrasonic Pulse Velocity

Tables 2 and 3 present the velocity of reinforced concrete with different steel diameters and cover thickness. In neglecting the influence of cover thickness, the velocity obtained from Eq. (12) is larger than the measurement velocity. However, the velocity obtained from British Standard Institution is closed to the measured velocity. Comparing with the velocity estimated from Eq. (12), the mean error of specimens with $w/c = 0.5$ is higher than that of specimens with $w/c = 0.6$. Hence, when ultrasonic wave propagates vertical to the steel direction, one can use ultrasonic pulse velocity to detect the steel within

reinforced concrete structures provided that the steel diameter is larger than or equal to 1.27 cm or the cover thickness is less than or equal to 6.23 cm.

Table 4 shows the velocity of corrosive damage of reinforced concrete structures. The velocity with corrosion is less than the velocity without corrosion. The velocity of corrosive specimen with $w/c = 0.5$ decreases 0.05 - 0.09 km/sec while the velocity of corrosive sample with $w/c = 0.6$ decreases 0.14 - 0.18 km/sec. Hence, one can use the ultrasonic pulse velocity to detect the corrosion of steel within reinforced concrete structures.

Ultrasonic Pulse Amplitude

Table 5 shows the reflective and transmission coefficient and decay value at interface between concrete and steel. Figures 3 - 4 show the results of ultrasonic pulse amplitude for A-team of reinforced concrete. From Figure 4 one knows that the decayed value of No. 8 without corrosive steel of reinforced concrete is ranged from 10 % to 15 %. This decayed value is lower than the theoretical value does. The less steel diameter, the lower decayed value. Hence, the decayed value of No. 5 without corrosive steel of reinforced concrete (see Figure 4) is lower than 5 %. If the steel number is lower than No. 5, then the ultrasonic pulse amplitude can not detect the existence of steel in reinforced concrete structures.

Figures 5 - 6 show the results of ultrasonic pulse amplitude for B-team reinforced concrete. The per-

Table 2. The ultrasonic pulse velocity of reinforced concrete with $w/c = 0.6$

Table 2. The ultrasonic pulse velocity of Reinforced concrete							
	Use different steel under the same diameter of sample			Use different diameter of sample under the same # 8			Mean error
Concrete velocity (km/sec)	4.33			4.41			
Steel No.	# 8	# 5	# 4	# 8	# 8	# 8	
Diameter of sample (cm)	10	10	10	10	12	15	
Measured velocity	4.77	4.62	4.53	4.71	4.65	4.56	
Velocity estimated from Eq. (12)	4.61	4.5	4.47	4.68	4.63	4.58	0.068
Velocity estimated from Eq. (13)	5.13	4.8	4.57	5.16	5.16	5.16	0.357
Velocity estimated from modified coefficient	4.71	4.58	4.53	4.79	4.75	4.68	0.067

Table 3. The ultrasonic pulse velocity of reinforced concrete with w/c = 0.5

	Use different steel under the same diameter of sample			Use different diameter of sample under the same # 8 steel			Mean error
Concrete velocity (km/sec)	4.47			4.54			
Steel No.	# 8	# 5	# 4	# 8	# 8	# 8	
Diameter of sample (cm)	10	10	10	10	12	15	
Measured velocity	4.85	4.75	4.65	4.81	4.78	4.7	
Velocity estimated from Eq. (12)	4.73	4.63	4.59	4.78	4.74	4.7	0.062
Velocity estimated from Eq. (13)	5.18	4.89	4.69	5.21	5.21	5.21	0.308
Velocity estimated from modified coefficient	4.86	4.73	4.68	4.93	4.89	4.82	0.068

Table 4. The velocity of corrosive damage of reinforced concrete structures A team: Sample diameter 10 cm with different steel No.

W/C	0.5			0.6		
Steel No.	# 8	# 5	# 4	# 8	# 5	# 4
Without corrosion	4.85	4.75	4.65	4.77	4.62	4.53
Saw type corrosion	4.85	4.74	4.66	4.77	4.7	4.53
Natural corrosion		4.74			4.6	

B team: use steel No. 8 with different sample diameter

Sample diameter	10	12	15	10	12	15
Without corrosion	4.81	4.78	4.7	4.71	4.65	4.56
With corrosion by using electric potential	4.72	4.73	4.63	4.57	4.51	4.38

Fig. 2. The relationship of decayed amplitude of reflective wave with color.

Fig. 3. Amplitude diagram of No. 8 without steel corrosion in the RC structures.

Fig. 4. Amplitude diagram of No. 5 without steel corrosion in the RC structures.

Fig. 5. Amplitude diagram without steel corrosion in the RC structures (diameter = 12 cm, W/C = 0.6, 62 dB).

Fig. 6. Amplitude diagram of steel corrosion in the RC structures with electric potential (diameter = 12 cm, W/C = 0.6, 62 dB).

Table 5. The reflective and transmission coefficient at interface between concrete and steel

Team	W/C	Concrete-Steel		Steel-Concrete		Decay value (%)
		R	D	R	D	
A	0.5	0.602	1.602	-0.602	0.398	36.24
	0.6	0.616	1.616	-0.616	0.384	37.95
B	0.5	0.592	1.592	-0.592	0.408	35.05
	0.6	0.062	1.602	-0.602	0.398	36.24

Table 6. Percent (%) of decayed amplitude of B team reinforcment concrete

W/C	0.5			0.6		
	10	12	15	10	12	15
Sample diameter (cm)	10	12	15	10	12	15
Without plus	80	70	55	80	70	60
electric potential						
With plus	50	55	20	55	35	15
electric potential						

cent of amplitude after decay is indicated in Table 6. Table 6 denotes that the sample diameter increases, the decayed value increases. Hence, one can use the ultrasonic pulse amplitude to predict the steel corrosion.

CONCLUSIONS

Based on ultrasonic pulse velocity and amplitude, the steel in reinforced concrete structures can be detected. Using equation (12) and Table 4, the measured pulse velocity of reinforced concrete structures is reliable. For measuring the corrosive steel in reinforced concrete structures, the corrosive steel modeled by the saw-shape reinforced concrete can not be detected whether steel corrosion or not by the method of ultrasonic pulse velocity. However, using ultrasonic pulse amplitude to measure the decayed value is larger (10 % - 15%) than the amplitude without steel corrosion does. After the steel corrodes, the crack is formed at the interface between steel and concrete. Therefore, the pulse velocity tends to decreasing and the decayed value of amplitude of reflective wave increases. Hence, both ultrasonic pulse velocity and amplitude can be used to measure the steel corrosion of reinforced concrete structures.

REFERENCES

1. Chung, H.W., "An Appraisal of the Ultrasonic Pulse Technique for Detecting Voids in Concrete," *Concrete*, Vol. 12, No. 11, London, Nov. pp. 25-28 (1978).
2. Bungey, J.H., "Effects of Steel on Ultrasonic Measurements for Concrete Members," *LABSE, Venice Symposium. Final Report*, pp. 93-100 (1983).
3. Burdekin, F.M., John, D.G., Payne, P.A, Smith, T.A, and Gaydecki, P.A "Nondestructive Methods for Field Inspection of Embedded or Encased High Strength Steel Rods and Cables," *NCHRP Project 10-30(3). Final Report*, Phase 2, May (1991).
4. Chung, H.W and Law, K.S. (1983), "Diagnosing in Situ Concrete by Ultrasonic Pulse Technique," *Concrete International*, October, pp. 42-49 (1983).
5. British Standard Institution "Recommendations for Non-destructive Methods of Test for Concrete - Measurement of the Velocity of Ultrasonic Pulse in Concrete," *BS 4408*, part 5, London, Feb (1974).

超音波檢測鋼筋混凝土結構物之腐蝕損傷

梁明德 黃然 江啟明

國立台灣海洋大學河海工程系所

摘要

本文的主要目的是採用超音波方法決定鋼筋混凝土構件之腐蝕損傷，使用ULCON3型探測儀及探頭（頻率：500kHz，直徑：20mm）量測速度及掃瞄混凝土表面預測腐蝕損傷，當鋼筋腐蝕時，超音波傳遞速度將因能量的消滅而引致波傳遞速度改變，利用超音波之脈波波速及振幅即可評估鋼筋混凝土之結構品質，由本研究可得到下列結論：(1)若鋼筋混凝土結構物之鋼筋腐蝕，則反射波之振幅將降低，(2)超音波之脈波波速及振幅可評估鋼筋混凝土結構物之鋼筋腐蝕程度，(3)發展超音波非破壞性檢測技術，可評估現場鋼筋混凝土結構物之生命週期。